



# 5600 Air-Dry Clear - ACCELERO

**ACCELERO**  
NORTH AMERICAN MARKET ONLY

## Product Description


Accelero 5600 is a conventional scratch resistant Air-Dry Clearcoat with premium finishing properties. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost reduction with no compromise on premium quality. It can be simply flattened and polished after 1 hour at application temperature.

It uses the same GenMax hardener family (H1522, H2232, H3236) as other premium clearcoats in the GenMax range, providing a complete and compact offer

## Suitable Substrates

- “General” GenRock Basecoat.
- “General” Gen2 O Basecoat.
- “General” GenVerde Basecoat.

## Product Application



100%	50%	10-15%
5600	H1522 2K HARDENER FAST	S1522 REDUCER
	<b>H2232 2K HARDENER NORMAL*</b>	<b>S2232 REDUCER*</b>
	H3236 2K HARDENER SLOW	S3236 REDUCER

*\*Recommended*



17 - 19 sec / DIN 4 mm / 20 °C (68 °F)  
Potlife: 60 minutes at 20°C



HVLP 1.2 – 1.3 mm  
2.0 – 2.2 bar inlet pressure

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



# 5600 Air-Dry Clear - ACCELERO

**ACCELERO**

NORTH AMERICAN MARKET ONLY



1 medium + 1 full coat  
3-5 minutes between coats  
35 – 45 micron



Dust Free After

15 min @ 25 °C (77°F)

25min@ 20 °C (68°F)

Touch Free After

20 min @ 25 °C (77°F)

45 min @ 20 °C (68°F)

Sandable and Polishable After


60 min @ 25 °C (77°F)

90 min @ 20 °C (68°F)

Important note: below 15°C, do not air-dry instead Low bake 5-10 minutes @ 60°C panel temperature



5 Minutes at 60°C (140 °F) Panel Temperature.



5-7 minutes, depending on color.

Substrate temperature 80°C-100°C (176°F to 212°F)

*Important note: keep panel at greater than 80cm from IR unit, depending on repair film thickness.*



Wear suitable protection

## Product Characteristics

**Specific Gravity:** 0.994 kg/cm<sup>3</sup> (8.29493 lbs/gal)

**Flash Point:** 25°C (77°F)

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



## 5600 Air-Dry Clear - ACCELERO

### ACCELERO

NORTH AMERICAN MARKET ONLY

<b>Solid Content:</b>	Approximately 48 % by weight RFU
<b>Coverage:</b>	7-8 m <sup>2</sup> /l at 35–45-micron film thickness (theoretical)
<b>SDS:</b>	Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.