



7021 – Ultra Performance Clear


Product Description

7021 is a VOC compliant high quality clearcoat that is easy to apply with excellent finishing properties whilst focusing on the efficiency of the bodyshop. A simple, half + full coat application process with no flash off, allows a repair to be ready to sand & polish in only an hour. “It uses the same hardener range as other premium clearcoats in the Genverde line, providing a complete and compact offer.”

Suitable Substrates

- “General” GenVerde Basecoat

Product Application




Mix 1:1 with H01522, H02232, H03236 hardener
Potlife: 35 minutes at 20°C



13-15 s / DIN 4 mm / 20o C



Compliant 1.3 – 1.4 mm (1/2 + full spray passes)
2.0 – 2.5 bar inlet pressure
0.7 bar at the air-cap



½ + 1 full = 40 – 50 micron

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



7021 – Ultra Performance Clear



	20°C
Dust Free	15-20 min
Tack Free	25-30 min
Dry for Sanding & Polishing	60-70 min



15 min. @ 40-45 oC panel temperature.
5 min. @ 60-65 oC panel temperature



Wear suitable protection

Product Characteristics

VOC:

Regulatory VOC 241.7 gr/lit (2.01 lbs/gal)
Regulatory VOC ready to spray < 250.0 gr/lit (2.08 lbs/gal)

Flash Point:

-4°C (24.8°F)

Specific Gravity:

1.05 kg/cm3

Solids Content:

77.3 % by weight

Coverage:

10 m2/l at 45 micron film thickness (theoretical)

SDS:

Refer to the Safety Data Sheet

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.