

## **Product Description**

This 2-coats high solid Scratch Resistant Clearcoat. 6100SR is very easy to apply and exhibits an excellent sag resistance while delivering a superior high gloss finish

#### **Suitable Substrates**

- GenRock basecoat
- Gen<sub>2</sub>O basecoat

#### **Product Application**

	100%	50%	0-5%
		H500 – FAST	S719
		H600 – NORMAL	S711 or S811
	6100SR	H700 – SLOW	S721 or S821
		H750 – EXTRA SLOW	S2040
		H760 - SPECIAL	S2050
<b>□</b> <b>↓</b>	16-18 sec / DIN 4 mm / 20 ° Potlife: 80 minutes at 20°C	°C (68 °F)	
	HVLP 1.3 – 1.5 mm (2 spray 2.0 - 2.5 bar inlet pressure		
	1 Medium – 1 full-Coat 50 – 60 micron		
<u>/†/†/</u>	5-7 minutes at 20 °C (68 °F)	between coats	

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.



# 6100SR- 2K Superior Clear



Low Bake at 30 mins at 60 °C panel temperature
Medium Long Wave 8 min The object should be maintained at greater than 80 cm from source.



Wear suitable protection

### **Product Characteristics**

VOC(2004/42/EC):	2004/42/EC IIB (e) (840)437. The EU limit value for this product (product category IIB. e) in ready to use form is max 840g/ltr. The VOC content of this product in ready for use form is max. 437 g/l.	
Specific Gravity:	1.009 kg/cm <sup>3</sup>	
Flash Point:	27°C	
Solid Content:	55.3 % by weight	
Coverage:	8 - 9 m <sup>2</sup> /l at 25-micron film thickness (theoretical)	
SDS:	Refer to the Safety Data Sheet	

Disclaimer: Users assume full responsibility for any consequences resulting from the incorrect usage of our products.

